

SPECIFICATIONS

ARTICLE

Designation : **Pickling paste**

Code bobet : **7035**

Selling Unit : **Unit**

Non-contractual pictures

**CHARACTERISTICS**

PICKLING PASTE BY APPLICATION FOR STAINLESS STEELS-
CHARACTERISTICS

AVESTA flux is used for the stripping removal of welding oxides and other ferritic contamination from operations such as welding, cutting, bending, grinding, etc.

It allows, simply and effectively, to preserve the corrosion resistance of treated materials.

INSTRUCTIONS FOR USE :

The product must be mixed before use.

On a cold part, apply using the brush code Bobet 1989 (sold separately) a coat of product on the area to be treated.

Processing temperature: 5-25C°

Leave to act for 30 minutes to 4 hours depending on the condition of the part, the steel grade, the temperature. If necessary, the product can remain overnight on the part. Rinse with a high-pressure jet neutralize the rinsing water.

HAZARD IDENTIFICATION :

- Corrosive product - toxic
- Wearing anti-acid clothing, gloves, boots, glasses, etc.
- Avoid contact with other metals: risk of nitrogen dioxide release.
- Do not work in a confined atmosphere

STANDARDS :

Compliant with Directive 2012/18/EU, Regulation 1907/2006 Annex XVII and Directive 2011/65/EU